

MOTIVE L16-AES

MODEL	L16-AES
VOLTAGE	6
CAPACITY	355Ah @ 20Hr
MATERIAL	Polypropylene
BATTERY	VRLA AGM / Non-Spillable / Maintenance-Free
COLOR	Maroon
WATERING	No Watering Required



6 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	TERMINAL TYPE	DIMENSIONS ° INCHES (mm)			WEIGHT I LBS. (kg)	HANDLES	INSTALLATION ORIENTATION
	903 L16-AES	M8/DT/LT	LENGTH	WIDTH	HEIGHT F		Braided Rope	Horizontal and Vertical
903			11.66 (296)	6.94 (176)	16.41 (417)	121 (55)		

ELECTRICAL SPECIFICATIONS

VOLTAGE	CRANKING PE	RFORMANCE	CAPACITY		CAPACITY ^B AMP-HOURS (Ah)		ENERGY (kWh)	INTERNAL RESISTANCE (m Ω)	SHORT CIRCUIT CURRENT (amps)		
G	C.C.A. ^D @0°F	C.A. ^e @32°F	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	17	2650
0	-	-	802	219	294	320	355	406	2.43	1.7	3650

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE 6V 12V 24V 36V 48V				48V	
Maximum Charge Current (A)	50% of C ₂₀				
Absorption Voltage (2.40 V/cell)	7.20	14.40	28.80	43.20	57.60
Float Voltage (2.25 V/cell)	6.75	13.50	27.00	40.50	54.00

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT						
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F						
OPERATIONAL DATA							


OPERATING TEMPERATURE	SELF DISCHARGE
-40°F to 140°F (-40°C to +60°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions

RECYCLE RESPONSIBLY




STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE


PERCENTAGE CHARGE	CELL	6 VOLT
100	2.14	6.42
75	2.09	6.27
50	2.04	6.12
25	1.99	5.97
0	1.94	5.82



BATTERY DIMENSIONS (shown with DT)



TERMINAL TYPE^G



A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are


The function of minutes of an entry when discharged at a constant rate at 60°F (27°C) and maintain a voltage above 1.75 Viceli. Capaciti Based on peak performance. B

0

С Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum. D. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.

PERCENT CAPACITY VS. TEMPERATURE 140 60 120 50 40 100 30 80 £ Û 20 60 Temperature Temperature 10 40 0 20 -10 0 -20 -20 -30 -40 -40 20% 40% 609 809 100% 120% 0% Percent of Available Capacity

SELF DISCHARGE VS. TIME[#]



E. C.A. (Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2 Vicel This is sometimes referred to a main crant and the second and the second and the second at 22 Well. This is sometimes referred to a main crant and any ango (32 27 F). Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.

G. Batteries in storage should be charged when they decline to 75% State of Charge (SOC).

Η. Weight may vary.

> ® Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.



F